

WEITACK® C5 HYDROCARBON RESIN

M100H

Properties:

C5 M100H is acid modified C5 with lighter color, used for Thermoplastic road marking paint and Hot melt adhesives.

Advantages:

- | | |
|--|-------------------------------|
| 1) light color | 2) Fine Flowing Ability |
| 3) High anti-abrasion and strong Dirt- resistant | 4) Fast drying speed of paint |
| 5) Sound heat stability | |

Specification:

Color (Gardner 1:1)	4 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	96-105	ASTM E 28
Color Stability (200'C, 2hrs, Gardner)	6 Max.	ASTM D 1544
Acid Value (KOHmg/g)	1.7 Max.	ASTM D 974
Melt Viscosity (200'C, cps)	150-250	ASTM D 3236

Typical Datas:

Softening Point (Ring & Ball, 'C)	100	ASTM E 28
Color (Gardner 1:1)	3	ASTM D 1544
Color Stability (200'C, Gardner 1:1)	5.5	ASTM D 1544
Acid Value (KOHmg/g)	1.5	ASTM D 974
Melt Viscosity (200'C, cps)	180	ASTM D 3236

Application

C5 M100H used for Thermoplastic road marking paint, which has a good compatibility with the rosin resin, EVA, etc., it can enhance the hardness, tenacity, and adhesive force of paint material and come to smooth coating surface.

C5 M100H can be used for Hot melt adhesives , with good compatibility with SIS, EVA, SBS.....

Package:

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com

1x20fcl = 10mts for 500kg big bags with pallets

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

This product information is indicative and does not include any guarantee.