

**WEITACK® C5 HYDROCARBON RESIN**

**MA6085**

**Properties:**

MA6085 is aromatic modified aliphatic hydrocarbon resin.

**Detailed Specification:**

|                                   |        |             |
|-----------------------------------|--------|-------------|
| Color (Gardner 1:1)               | 9 Max. | ASTM D 1544 |
| Softening Point (Ring & Ball, 'C) | 95-105 | ASTM E 28   |
| Melt Viscosity (200'C, cps)       | 70-150 | ASTM D 3236 |

**Typical Datas:**

|                                   |      |             |
|-----------------------------------|------|-------------|
| Softening Point (Ring & Ball, 'C) | 100  | ASTM E 28   |
| Color (Gardner 1:1)               | 8.5  | ASTM D 1544 |
| Melt Viscosity (200'C, cps)       | 100  | ASTM D 3236 |
| Mn                                | 800  | GPC         |
| Mw                                | 2100 | GPC         |

**Application:**

MA6085 mainly used as tackifier for HMA, Hot Melt PSA, Solvent base PSA. with Sound compatibility with base polymers like EVA, SIS, natural rubber and Butyl rubber.....

**Package:**

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags with pallets

**Storage:**

Keep resin in ventilation place and away from heater, Temperature not exceeding 30°C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

**Notice:**

**This product information is indicative and does not include any guarantee.**