

WEITACK® C5 HYDROCARBON RESIN

MA6095

Properties:

MA6095 is low color aromatic modified aliphatic hydrocarbon resin.

Advantages:

Sound compatibility with base polymers than normal C5 resin

Specification:

Color (Gardner 1:1)	3 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	90-95	ASTM E 28
Acid Value (KOHmg/g)	1.0 Max.	ASTM D 974
Melt Viscosity (200'C, cps)	70-100	ASTM D 3236

Typical Datas:

Specific Gravity (20/20oC)	0.97	ASTM D 71
Softening Point (Ring & Ball, 'C)	92	ASTM E 28
Color (Gardner 1:1)	3	ASTM D 1544
Color Stability (200'C,2 hous Gardner 1:1)	6	ASTM D 1544
Acid Value (KOHmg/g)	0.02	ASTM D 974
Melt Viscosity (200'C, cps)	85	ASTM D 3236
Mw	2000	GPC
Mn	1100	GPC

Application:

MA6095 used as tackifier in Pressure Sensitive Adhesives and Hot Melt Adhesive. Well balanced the properties of PSA, like adhesion, adhesion strength and cohesive strength.

Package

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30°C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

This product information is indicative and does not include any guarantee.

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com