

WEITACK® C5 HYDROCARBON RESIN

MA6104

Properties:

MA6104 is low molecular aliphatic hydrocarbon resin, Sound compatibility with Natural Rubber, many kinds of synthetic rubber, styrene polymers (SIS, SEBS and SBS)

Detailed Specification:

Color (Gardner 1:1)	3 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	96-105	ASTM E 28
Melt Viscosity (200'C, cps)	100-150	ASTM D 3236
Wax Cloud Point 'C (22.5/32.5/45)	85 Max	

Typical Datas:

Softening Point (Ring & Ball, 'C)	100	ASTM E 28
Color (Gardner 1:1)	3	ASTM D 1544
Color Stability (200'C,2hours Gardner 1:1)	6	ASTM D 1544
Melt Viscosity (200'C, cps)	120	ASTM D 3236
Wax Cloud Point 'C (22.5/32.5/45)	80	
Insoluble Vol% (180'C 1 hr)	0.01	
Mn	1300	GPC

Application:

MA6104 used as tackifier in Pressure Sensitive Adhesives and Hot Melt Adhesive. Solvent Based Natural Rubber Pressure Sensitive Adhesive labels and tapes.

Package:

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

This product information is indicative and does not include any guarantee.

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com