

WEITACK® C5 HYDROCARBON RESIN

MA6106

Properties:

MA6106 is low molecular weight aliphatic hydrocarbon resin. Obtained by an unsaturated hydrocarbon and olefin polymerization, with fine color and stability.

Detailed Specification:

Color (Gardner 1:1)	4 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	96-105	ASTM E 28
Melt Viscosity (200'C, cps)	60-150	ASTM D 3236

Typical Datas:

Softening Point (Ring & Ball, 'C)	100	ASTM E 28
Color (Gardner 1:1)	3	ASTM D 1544
Color Stability (200'C, Gardner 1:1)	5	ASTM D 1544
Acid Value (KOHmg/g)	0.02	ASTM D 974
Melt Viscosity (200'C, cps)	125	ASTM D 3236
Mn	1200	GPC
Mw	2500	GPC

Application:

MA6106 used for Pressure sensitive adhesives, Tapes, Labels, Casting wax.... with Sound compatibility with base polymers like SIS

Package:

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags with pallets

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

This product information is indicative and does not include any guarantee.