

**WEITACK® C5 HYDROCARBON RESIN**

**MA6115**

**Properties:**

MA6115 is aliphatic hydrocarbon resin obtained from polymerizing unsaturated aliphatic olefins or diolefins, with higher Softening point.

**Detailed Specification:**

Color (Gardner 1:1)	5 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	110- 117	ASTM E 28
Acid Value (KOH mg/g)	0.5 max	ASTM D 1639

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	115	ASTM E 28
Color (Gardner 1:1)	4	ASTM D 1544
Acid Value (KOH mg/g)	0.1	ASTM D 1639
Mn	1400	GP
Mw	2600	G

**Application:**

MA6115 mainly used as tackifier for solvent base PSA. with Sound compatibility with base polymers like EVA, SIS,metallocene polyolefins, natural rubber, synthetic polyisoprene and Butyl rubber

**Package:**

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags with pallets

**Storage:**

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

**Notice:**

**This product information is indicative and does not include any guarantee.**