

**WEITACK® C9 HYDROCARBON RESIN**

**WP140**

**Properties:**

**C9 WP140**, is molecular weight thermoplastic aromatic resin from C9 fraction. with the color of lighter yellow. Good solubility, mutual solubility, water resistance, excellent chemical stability over acid and alkali, good adhesive strength, and low heat conduction.

**Detailed Specification:**

Color (Gardner 1:1)	5- 9	ASTM D 1544
Softening Point (Ring & Ball, 'C)	130-140	ASTM E 28
Acid Value (KOHmg/g)	0.5max	ASTM D 974

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	136	ASTM E 28
Color (Gardner 1:1)	7, 8, 9	ASTM D 1544
Acid Value (KOHmg/g)	0.1	ASTM D 974
Ash %	0.01	ASTM D1063
Bromine	20	
Iodine g I2/100g	20	

**Applications:**

1. **Adhesive:** it can increase bonding strength, resistance of acid, alkali and water of the adhesive and pressure-sensitive Tape.
2. **Printing ink:** It can increase the printing quality with quick drying and brighter.

**Package:**

25kg plastic or kraft bags , 750kg big bags  
1x20fcl = 18mts without pallets, 15mts with pallets for 25kg bags

**Storage:** Keep resin in ventilation place and away from heater

**Notice:**

This product information is indicative and does not include any guarantee.

**ADD:** 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: [sales@weichemresin.com](mailto:sales@weichemresin.com) [www.weichemresin.com](http://www.weichemresin.com)