

WEITACK® C9 HYDROCARBON RESIN

WP150

Properties:

C9 WP150, is molecular weight thermoplastic aromatic resin from C9 fraction. with the color of lighter yellow. Good solubility, mutual solubility, water resistance, excellent chemical stability over acid and alkali, good adhesive strength, and low heat conduction.

Detailed Specification:

Color (Gardner 1:1)	8-9	ASTM D 1544
Softening Point (Ring & Ball, 'C)	135-145	ASTM E 28
Acid Value (KOHmg/g)	0.5 max	ASTM D 974

Typical Datas:

Softening Point (Ring & Ball, 'C)	142	ASTM E 28
Color (Gardner 1:1)	8, 9	ASTM D 1544
Acid Value (KOHmg/g)	0.1	ASTM D 974
Ash %	0.01	ASTM D1063
Bromine	20	
Iodine g I2/100g	20	

Applications:

1. **Adhesive:** it can increase bonding strength, resistance of acid, alkali and water of the adhesive and pressure-sensitive Tape.
2. **Printing ink:** It can increase the printing quality with quick drying and brighter.

Package:

25kg plastic or kraft bags , 750kg big bags
1x20fcl = 18mts without pallets, 15mts with pallets for 25kg bags

Storage: Keep resin in ventilation place and away from heater

Notice:

This product information is indicative and does not include any guarantee.

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com