

**WEITACK® DCPD RESIN**

**MD100**

**Properties:**

**MD100** is DCPD resin. It is obtained from polymerization of cyclic ingredients. Good compatibility with base polymers such as EVA, SIS and SBC..

**Detailed Specification:**

Color (Gardner 1:1)	6	ASTM D 1544
Softening Point (Ring & Ball, 'C)	98-108	ASTM E 28

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	102	ASTM E 28
Color (Gardner 1:1)	4-5	ASTM D 1544
Acid Value (KOHmg/g)	0.2	ASTM D 974
Ash %	0.01	ASTM D1063

**Application:**

Used as tacky resins for rubbers and tires, etc.

**Packing:**

25kg Kraft bags , 500kg big bags

1x20fcl = 18mts without pallets and 15mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags

**Storage:**

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump