

WEITACK® DCPD HYDROGENATED RESIN

MDH130

Properties:

MDH130 is hydrogenated DCPD resin. It is obtained from polymerization and hydrogenation of cyclic ingredients. Good compatibility with base polymers such as EVA, SIS and SBC..

Detailed Specification:

Color (Gardner 1:1)	0	ASTM D 1544
Softening Point (Ring & Ball, 'C)	126-135	ASTM E 28
Melt Viscosity (200'C, cps)	300-700 Max.	ASTM D 3236

Typical Datas:

Specific Gravity (20/20'C)	1.08	ASTM D 71
Softening Point (Ring & Ball, 'C)	130	ASTM E 28
Color (Gardner 1:1)	0	ASTM D 1544
Acid Value (KOHmg/g)	0.02	ASTM D 974
Melt Viscosity (200'C, cps)	500	ASTM D 3236
Ash %	0.01	ASTM D 1063

Application:

Used as tacky resins for hot-melt adhesives, hot melt pressure-sensitive and sealants.

Packing:

25kg Kraft bags , 500kg big bags

1x20fcl = 16.5mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump

Notice:

This product information is indicative and does not include any guarantee.