

**WEITACK® C9 HYDROGENATED RESIN**

**MH890**

**Properties:**

**C9 MH890** is water white thermoplastic hydrocarbon resin, a polymerization obtain from raw materials circulation hydrogenation process, with good heat resistance, and sound compatibility with EVA, SBC and other polymers ,

**Detailed Specification:**

Color (Gardner 1:1)	0	ASTM D 1544
Softening Point (Ring & Ball, 'C)	85-95'C	ASTM E 28
Acid Value (KOHmg/g)	0.05 Max.	ASTM D 974
Melt Viscosity (190'C cps)	200 Max	ASTM D 3236

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	90	ASTM E 28
Color (Gardner 1:1)	0	ASTM D 1544
Melt Viscosity (190'C cps)	75	ASTM D 3236
Acid Value (KOHmg/g)	0.02	ASTM D 974

**Application:**

MH890 mainly used in the production of adhesive, hot melt adhesive, pressure sensitive adhesive and rubber adhesive tackifying resin; paper sizing agent, Ink color development agent and connecting material.

MH890 emulsion emulsified with neoprene latex miscible made adhesion and Strong weather ability of exterior wall paint, antirust paint ;and emulsified asphalt waterproof coating can be prepared miscible;

MH890 Used as a foundry binder can improve casting yield.

MH890 Used in the production of sanitary napkins, diapers and other series products.

**Package:**

25kg kraft bags , 700kg big bags

1x20fcl = 17mts without pallets, 14mts with pallets for 25kg bags

**Storage:**

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is

**ADD:** 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: [sales@weichemresin.com](mailto:sales@weichemresin.com) [www.weichemresin.com](http://www.weichemresin.com)

---

recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

**Notice:**

**This product information is indicative and does not include any guarantee.**