

WEITACK® C9 HYDROGENATED RESIN

MH900

Properties:

C9 MH900 is water white thermoplastic hydrocarbon resin, a polymerization obtain from raw materials circulation hydrogenation process, with good heat resistance, and sound compatibility with EVA, SBC and other polymers ,

Detailed Specification:

Color (Gardner 1:1)	0	ASTM D 1544
Softening Point (Ring & Ball, 'C)	100-110'C	ASTM E 28
Acid Value (KOHmg/g)	0.05 Max.	ASTM D 974
Melt Viscosity (150'C cps)	500-1000	ASTM D 3236

Typical Datas:

Specific Gravity (20/20oC)	1.08	ASTM D 71
Softening Point (Ring & Ball, 'C)	100	ASTM E 28
Color (Gardner 1:1)	0	ASTM D 1544
Melt Viscosity (150'C cps)	750	ASTM D 3236
Acid Value (KOHmg/g)	0.02	ASTM D 974
Ash %	0.01	ASTM D1063
Cloudy point 'C	75	
Insoluble Vol% (180'C 1 hr)	0.01	

Application:

MH900 mainly used in the production of adhesive, hot melt adhesive, pressure sensitive adhesive and rubber adhesive tackifying resin; paper sizing agent, Ink color development agent and connecting material.

MH900 emulsion emulsified with neoprene latex miscible made adhesion and Strong weather ability of exterior wall paint, antirust paint ;and emulsified asphalt waterproof coating can be prepared miscible;

MH900Used as a foundry binder can improve casting yield.

MH900 Used in the production of sanitary napkins, diapers and other series products.

Package:

25kg kraft bags , 700kg big bags

1x20fcl = 18mts without pallets, 15mts with pallets for 25kg bags

1x20fcl= 14mts for 700kgs bags

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

This product information is indicative and does not include any guarantee.

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com