

**WEITACK® C9 HYDROGENATED RESIN**

**MH940**

**Properties:**

**C9 MH940** is water white aromatic thermoplastic hydrocarbon resin, a polymerization obtain from raw materials circulation hydrogenation process, with good heat resistance, and sound compatibility with EVA,SIS and PE,PP, BOPP, BP, APAO ...

**Detailed Specification:**

Color (Gardner 1:1)	0	ASTM D 1544
Softening Point (Ring & Ball, 'C)	135-145'C	ASTM E 28
Molecular Weight: Mn	600	
Molecular Weight: Mw	950	

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	140	ASTM E 28
Color (Gardner 1:1)	0	ASTM D 1544
Insoluble Vol% (180'C 1 hr)	0.03	

**Application:**

1. Used for plastic modification .
2. Used for hot melt adhesive, pressure sensitive adhesive and rubber adhesive tackifier resin;

**Package:**

25kg kraft bags , 500kg big bags  
1x20fcl = 14mts without pallets, 17mts without pallets for 25kg bags  
1x20fcl= 10mts for 500kgs bags with pallets  
1x40fcl=20mts for 500kg bags with pallets. and 28mts for 25kg bags with pallets.

**Storage:**

Keep resin in ventilation place and away from heater,

**Notice:**

This product information is indicative and does not include any guarantee.

**ADD:** 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: [sales@weichemresin.com](mailto:sales@weichemresin.com) [www.weichemresin.com](http://www.weichemresin.com)