

WEITACK® Terpene Resin T100

Properties:

T100 is 100% pure terpene resin, used for Tapes, PSA, HMA. It is suitable for preparing adhesive mainly made from SIS. Has excellent compatibility with the thermoplastic elastomer SIS, SBS, SEBS, natural rubber. many kinds of synthetic rubber, EVA, as well as other tackifier resin

Detailed Specification:

| | | |
|-----------------------------------|----------|-------------|
| Color (Gardner 1:1) | 6 Max. | ASTM D 1544 |
| Softening Point (Ring & Ball, 'C) | 95-105 | ASTM E 28 |
| Acid Value (KOHmg/g) | 1.0 Max. | ASTM D 974 |
| Toluene insoluble substance % | 0.05 | |

Typical Datas:

| | | |
|-----------------------------------|------|-------------|
| Color (Gardner 1:1) | 5 | ASTM D 1544 |
| Softening Point (Ring & Ball, 'C) | 105 | ASTM E 28 |
| Acid Value (KOHmg/g) | 0.5 | ASTM D 974 |
| Toluene insoluble substance % | 0.03 | |

Application: Hot melt pressure sensitive adhesive

Hot melt adhesive , solvent based pressure sensitive adhesive

Packing: 25kg Kraft bags , 500kg big bags

1x20fcl = 16mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags

Storage:

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

Notice:

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA

TEL: 86-532-85721337, 85720052

Email: sales@weichemresin.com www.weichemresin.com

This product information is indicative and does not include any guarantee.

ADD: 603-1-3 , NO.63, MIDDLE HONGKONG ROAD, QINGDAO 266071, CHINA
TEL: 86-532-85721337, 85720052
Email: sales@weichemresin.com www.weichemresin.com